



ARCHITECTURAL SPECIFICATIONS GUIDE

CONCO PAINTS
Pro Technology...Engineered For The Job®



Interior Surface and Specification Selection

INTERIOR PLASTER, GYPSUM, KEENE'S CEMENT

Surface & Area	Veh.	Sheen	Finished Coat	Primer	Gloss Units	Sq.ft./Gal. (smooth)	Mils DFT	% Solids By Vol.	% Solids By Wt.	Drying Time:	
										To Touch	To Recoat
Walls & Ceilings	Latex	Flat	9500 Int/Ext Series	P001 Drywall PVA Primer/Sealer OR P007 All Surface Acrylic Stainblocking Primer OR P015 Latex High Build Primer/Surfacer	0-5@85°	400	1.3	32	43	1 Hr.	4 Hrs.
			1000 Int Series		0-2@85°	400	1.3	33	53	1 Hr.	4 Hrs.
			160 Int Pure Low Odor		0-5@85°	400	1.6	41	59	1 Hr.	4 Hrs.
			100 Int Series		0-2@85°	400	1.2	30	49	1 Hr.	4 Hrs.
			10 Int Series		0-5@85°	400	1.0	26	43	1 Hr.	4 Hrs.
			1E Int Builder Maintenance		0-10@85°	400	1.0	25	45	1 Hr.	4 Hrs.
	Latex	Eggshell	1500 Int Series	(same)	20-30@85°	400	1.3	33	46	1 Hr.	4 Hrs.
			150 Int Series	(same)	20-30@85°	400	1.3	32	44	1 Hr.	4 Hrs.
	Latex	Satin	2000 Int Series	(same)	5-15@60°	400	1.6	40	52	1 Hr.	4 Hrs.
			200 Int Series	(same)	5-15@60°	400	1.4	34	46	1 Hr.	4 Hrs.
			180 Int Pure Low Odor	(same)	10-20@85°	400	1.6	41	55	1 Hr.	4 Hrs.
	Alkyd	Semi-Gloss	9000 Int/Ext Series	(same)	70+@60°	400	2.2	54	72	4-5 Hrs.	12-18 Hrs.
	Latex	Semi-Gloss	3000 Int Series	(same)	35-45@60°	400	1.5	37	49	1 Hr.	4 Hrs.
			300 Int Series	(same)	35-45@60°	400	1.1	27	36	1 Hr.	4 Hrs.
			190 Int Pure Low Odor	(same)	35-45@60°	400	1.6	39	51	1 Hr.	4 Hrs.
			30 Int Series	(same)	35-45@60°	400	1.1	28	37	1 Hr.	4 Hrs.

INTERIOR DRYWALL

Surface & Area	Veh.	Sheen	Finished Coat	Primer	Gloss Units	Sq.ft./Gal. (smooth)	Mils DFT	% Solids By Vol.	% Solids By Wt.	Drying Time:	
										To Touch	To Recoat
Walls & Ceilings, Gypsum Board, Wood Pulp Board, Etc.	Latex	Flat	9500 Int/Ext Series	P001 Drywall PVA Primer/Sealer OR P007 All Surface Acrylic Stainblocking Primer OR P015 Latex High Build Primer/Surfacer	0-5@85°	400	1.3	32	43	1 Hr.	4 Hrs.
			1000 Int Series		0-2@85°	400	1.3	33	53	1 Hr.	4 Hrs.
			160 Int Pure Low Odor		0-5@85°	400	1.6	41	59	1 Hr.	4 Hrs.
			100 Int Series		0-2@85°	400	1.2	30	49	1 Hr.	4 Hrs.
			10 Int Series		0-5@85°	400	1.0	26	43	1 Hr.	4 Hrs.
			1E Int Builder Maintenance		0-10@85°	400	1.0	25	45	1 Hr.	4 Hrs.
	Latex	Eggshell	1500 Int Series	(same)	20-30@85°	400	1.3	33	46	1 Hr.	4 Hrs.
			150 Int Series	(same)	20-30@85°	400	1.3	32	44	1 Hr.	4 Hrs.
	Latex	Satin	2000 Int Series	(same)	5-15@60°	400	1.6	40	52	1 Hr.	4 Hrs.
			200 Int Series	(same)	5-15@60°	400	1.4	34	46	1 Hr.	4 Hrs.
			180 Int Pure Low Odor	(same)	10-20@85°	400	1.6	41	55	1 Hr.	4 Hrs.
	Alkyd	Semi-Gloss	9000 Int/Ext Series	(same)	70+@60°	400	2.2	54	72	4-5 Hrs.	12-18 Hrs.
	Latex	Semi-Gloss	3000 Int Series	(same)	35-45@60°	400	1.5	37	49	1 Hr.	4 Hrs.
			300 Int Series	(same)	35-45@60°	400	1.1	27	36	1 Hr.	4 Hrs.
			190 Int Pure Low Odor	(same)	35-45@60°	400	1.6	39	51	1 Hr.	4 Hrs.
			30 Int Series	(same)	35-45@60°	400	1.1	28	37	1 Hr.	4 Hrs.

INTERIOR WOOD

Surface & Area	Veh.	Sheen	Finished Coat	Primer	Gloss Units	Sq.ft./Gal. (smooth)	Mils DFT	% Solids By Vol.	% Solids By Wt.	Drying Time:		
										To Touch	To Recoat	
Ceilings, Doors, Trim, Cabinets, Work Partitions, Frames	Latex	Flat	9500 Int/Ext Series	P001 Drywall PVA Primer/Sealer OR P007 All Surface Acrylic Stainblocking Primer	0-5@85°	400	1.3	32	43	1 Hr.	4 Hrs.	
			1000 Int Series		0-2@85°	400	1.3	33	53	1 Hr.	4 Hrs.	
			160 Int Pure Low Odor		0-5@85°	400	1.6	41	59	1 Hr.	4 Hrs.	
			100 Int Series		0-2@85°	400	1.2	30	49	1 Hr.	4 Hrs.	
			10 Int Series		0-5@85°	400	1.0	26	43	1 Hr.	4 Hrs.	
			1E Int Builder Maintenance		(same)	0-10@85°	400	1.0	25	45	1 Hr.	4 Hrs.
	Latex	Eggshell	1500 Int Series	(same)	20-30@85°	400	1.3	33	46	1 Hr.	4 Hrs.	
			150 Int Series	(same)	20-30@85°	400	1.3	32	44	1 Hr.	4 Hrs.	
	Latex	Satin	2000 Int Series	(same)	5-15@60°	400	1.6	40	52	1 Hr.	4 Hrs.	
			200 Int Series	(same)	5-15@60°	400	1.4	34	46	1 Hr.	4 Hrs.	
			180 Int Pure Low Odor	(same)	10-20@85°	400	1.6	41	55	1 Hr.	4 Hrs.	
	Alkyd	Semi-Gloss	9000 Int/Ext Series	(same)	70+@60°	400	2.2	54	72	4-5 Hrs.	12-18 Hrs.	
	Latex	Semi-Gloss	3000 Int Series	(same)	35-45@60°	400	1.5	37	49	1 Hr.	4 Hrs.	
			300 Int Series	(same)	35-45@60°	400	1.1	27	36	1 Hr.	4 Hrs.	
			190 Int Pure Low Odor	(same)	35-45@60°	400	1.6	39	51	1 Hr.	4 Hrs.	
			30 Int Series	(same)	35-45@60°	400	1.1	28	37	1 Hr.	4 Hrs.	
	Floors	Alkyd	Gloss	9300 Int/Ext Floor Enamel	None	85+@60°	400	2.2	55	68	6-8 Hrs.	24 Hrs.

INTERIOR ACCOUSTICAL

Surface & Area	Veh.	Sheen	Finished Coat	Primer	Gloss Units	Sq.ft./Gal. (smooth)	Mils DFT	% Solids By Vol.	% Solids By Wt.	Drying Time:	
										To Touch	To Recoat
Perforated Fiberboard	Latex	Flat	9500 Int/Ext Series	P001 Drywall PVA Primer/Sealer OR P007 All Surface Acrylic Stainblocking Primer	0-5@85°	400	1.3	32	43	1 Hr.	4 Hrs.
			1000 Int Series		0-2@85°	400	1.3	33	53	1 Hr.	4 Hrs.
			160 Int Pure Low Odor		0-5@85°	400	1.6	41	59	1 Hr.	4 Hrs.
			100 Int Series		0-2@85°	400	1.2	30	49	1 Hr.	4 Hrs.
			10 Int Series		0-5@85°	400	1.0	26	43	1 Hr.	4 Hrs.
			1E Int Builder Maintenance		(same)	0-10@85°	400	1.0	25	45	1 Hr.

Please refer to the Product Data Sheet for proper surface preparation and application guidelines.



Interior Surface and Specification Selection

INTERIOR MASONRY												
Surface & Area	Veh.	Sheen	Finished Coat	Primer	Gloss Units	Sq.ft./Gal. (smooth)	Mils DFT	% Solids By Vol.	% Solids By Wt.	Drying Time:		
										To Touch	To Recoat	
Walls & Ceilings, Concrete Block, Poured Concrete, Precast Concrete, Unglazed Brick & Tile	Latex	Flat	9500 Int/Ext Series	P001 Drywall PVA Primer/Sealer OR P007 All Surface Acrylic Stainblocking Primer OR P9511 Acrylic Latex Block Filler (for block)	0-5@85°	400	1.3	32	43	1 Hr.	4 Hrs.	
			1000 Int Series		0-2@85°	400	1.3	33	53	1 Hr.	4 Hrs.	
			160 Int Pure Low Odor		0-5@85°	400	1.6	41	59	1 Hr.	4 Hrs.	
			100 Int Series		0-2@85°	400	1.2	30	49	1 Hr.	4 Hrs.	
			10 Int Series		0-5@85°	400	1.0	26	43	1 Hr.	4 Hrs.	
			1E Int Builder Maintenance		0-10@85°	400	1.0	25	45	1 Hr.	4 Hrs.	
	Latex	Eggshell	1500 Int Series	(same)	20-30@85°	400	1.3	32	44	1 Hr.	4 Hrs.	
			150 Int Series	(same)	20-30@85°	400	1.3	32	44	1 Hr.	4 Hrs.	
	Latex	Satin	2000 Int Series	(same)	5-15@60°	400	1.6	40	52	1 Hr.	4 Hrs.	
			200 Int Series	(same)	5-15@60°	400	1.4	34	46	1 Hr.	4 Hrs.	
			180 Int Pure Low Odor	(same)	10-20@85°	400	1.6	41	55	1 Hr.	4 Hrs.	
	Alkyd	Semi-Gloss	9000 Int/Ext Series	(same)	70+@60°	400	2.2	54	72	4-5 Hrs.	12-18 Hrs.	
	Latex	Semi-Gloss	3000 Int Series	(same)	35-45@60°	400	1.5	37	49	1 Hr.	4 Hrs.	
			300 Int Series	(same)	35-45@60°	400	1.1	27	36	1 Hr.	4 Hrs.	
			190 Int Pure Low Odor	(same)	35-45@60°	400	1.6	39	51	1 Hr.	4 Hrs.	
			30 Int Series	(same)	35-45@60°	400	1.1	28	37	1 Hr.	4 Hrs.	
	Floors	Alkyd	Gloss	9300 Int/Ext Floor Enamel	None	85+@60°	400	2.2	55	68	6-8 Hrs.	24 Hrs.

INTERIOR METAL												
Surface & Area	Veh.	Sheen	Finished Coat	Primer	Gloss Units	Sq.ft./Gal. (smooth)	Mils DFT	% Solids By Vol.	% Solids By Wt.	Drying Time:		
										To Touch	To Recoat	
Walls, Ceilings, Doors, Windows, Structural Steel, Ornamental Iron Trim, Ducts, Copper, Non-Galvanized Metal	Latex	Flat	9500 Int/Ext Series	P007 All Surface Acrylic Stainblocking Primer	0-5@85°	400	1.3	32	43	1 Hr.	4 Hrs.	
			1000 Int Series		0-2@85°	400	1.3	33	53	1 Hr.	4 Hrs.	
			160 Int Pure Low Odor		0-5@85°	400	1.6	41	59	1 Hr.	4 Hrs.	
			100 Int Series		(same)	0-2@85°	400	1.2	30	49	1 Hr.	4 Hrs.
			10 Int Series		(same)	0-5@85°	400	1.0	26	43	1 Hr.	4 Hrs.
			1E Int Builder Maintenance		(same)	0-10@85°	400	1.0	25	45	1 Hr.	4 Hrs.
	Latex	Eggshell	1500 Int Series	(same)	20-30@85°	400	1.3	33	46	1 Hr.	4 Hrs.	
			150 Int Series	(same)	20-30@85°	400	1.3	32	44	1 Hr.	4 Hrs.	
	Latex	Satin	2000 Int Series	(same)	5-15@60°	400	1.6	40	52	1 Hr.	4 Hrs.	
			200 Int Series	(same)	5-15@60°	400	1.4	34	46	1 Hr.	4 Hrs.	
			180 Int Pure Low Odor	(same)	10-20@85°	400	1.6	41	55	1 Hr.	4 Hrs.	
	Alkyd	Semi-Gloss	9000 Int/Ext Series	(same)	70+@60°	400	2.2	54	72	4-5 Hrs.	12-18 Hrs.	
	Latex	Semi-Gloss	3000 Int Series	(same)	35-45@60°	400	1.5	37	49	1 Hr.	4 Hrs.	
			300 Int Series	(same)	35-45@60°	400	1.1	27	36	1 Hr.	4 Hrs.	
			190 Int Pure Low Odor	(same)	35-45@60°	400	1.6	39	51	1 Hr.	4 Hrs.	
			30 Int Series	(same)	35-45@60°	400	1.1	28	37	1 Hr.	4 Hrs.	
	Galvanized Metal	Latex	Flat	9500 Int/Ext Series	(same)	0-5@85°	400	1.3	32	43	1 Hr.	4 Hrs.
				1000 Int Series		0-2@85°	400	1.3	33	53	1 Hr.	4 Hrs.
160 Int Pure Low Odor				0-5@85°		400	1.6	41	59	1 Hr.	4 Hrs.	
100 Int Series				0-2@85°		400	1.2	30	49	1 Hr.	4 Hrs.	
10 Int Series				0-5@85°		400	1.0	26	43	1 Hr.	4 Hrs.	
1E Int Builder Maintenance				0-10@85°		400	1.0	25	45	1 Hr.	4 Hrs.	
Latex		Eggshell	1500 Int Series	(same)	20-30@85°	400	1.3	33	46	1 Hr.	4 Hrs.	
			150 Int Series	(same)	20-30@85°	400	1.3	32	44	1 Hr.	4 Hrs.	
Latex		Satin	2000 Int Series	(same)	5-15@60°	400	1.6	40	52	1 Hr.	4 Hrs.	
			200 Int Series	(same)	5-15@60°	400	1.4	34	46	1 Hr.	4 Hrs.	
			180 Int Pure Low Odor	(same)	10-20@85°	400	1.6	41	55	1 Hr.	4 Hrs.	
Alkyd		Semi-Gloss	9000 Int/Ext Series	(same)	70+@60°	400	2.2	54	72	4-5 Hrs.	12-18 Hrs.	
Latex		Semi-Gloss	3000 Int Series	(same)	35-45@60°	400	1.5	37	49	1 Hr.	4 Hrs.	
			300 Int Series	(same)	35-45@60°	400	1.1	27	36	1 Hr.	4 Hrs.	
			190 Int Pure Low Odor	(same)	35-45@60°	400	1.6	39	51	1 Hr.	4 Hrs.	
			30 Int Series	(same)	35-45@60°	400	1.1	28	37	1 Hr.	4 Hrs.	
Aluminum		Latex	Flat	9500 Int/Ext Series	None	0-5@85°	400	1.3	32	43	1 Hr.	4 Hrs.
				1000 Int Series		0-2@85°	400	1.3	33	53	1 Hr.	4 Hrs.
	160 Int Pure Low Odor			0-5@85°		400	1.6	41	59	1 Hr.	4 Hrs.	
	100 Int Series			0-2@85°		400	1.2	30	49	1 Hr.	4 Hrs.	
	10 Int Series			0-5@85°		400	1.0	26	43	1 Hr.	4 Hrs.	
	1E Int Builder Maintenance			0-10@85°		400	1.0	25	45	1 Hr.	4 Hrs.	
	Latex	Eggshell	1500 Int Series	None	20-30@85°	400	1.3	33	46	1 Hr.	4 Hrs.	
			150 Int Series	None	20-30@85°	400	1.3	32	44	1 Hr.	4 Hrs.	
	Latex	Satin	2000 Int Series	None	5-15@60°	400	1.6	40	52	1 Hr.	4 Hrs.	
			200 Int Series	None	5-15@60°	400	1.4	34	46	1 Hr.	4 Hrs.	
			180 Int Pure Low Odor	None	10-20@85°	400	1.6	41	55	1 Hr.	4 Hrs.	
	Alkyd	Semi-Gloss	9000 Int/Ext Series	P007 All Surface Acrylic Stainblocking Primer	70+@60°	400	2.2	54	72	4-5 Hrs.	12-18 Hrs.	
	Latex	Semi-Gloss	3000 Int Series	None	35-45@60°	400	1.5	37	49	1 Hr.	4 Hrs.	
			300 Int Series	None	35-45@60°	400	1.1	27	36	1 Hr.	4 Hrs.	
			190 Int Pure Low Odor	None	35-45@60°	400	1.6	39	51	1 Hr.	4 Hrs.	
			30 Int Series	None	35-45@60°	400	1.1	28	37	1 Hr.	4 Hrs.	



Exterior Surface and Specification Selection

EXTERIOR WOOD											
Surface & Area	Veh.	Sheen	Finished Coat	Primer	Gloss Units	Sq.ft./Gal. (smooth)	Mils DFT	% Solids By Vol.	% Solids By Wt.	Drying Time:	
										To Touch	To Recoat
Siding, Trim, Shingles, Shakes, Rough Sawn Lumber, Shutters, Sash, Doors, Misc. Wood	Latex	Flat	9500 Int/Ext Series	P007 All Surface	0-5@85°	400	1.3	32	43	1 Hr.	4 Hrs.
			5000 Ext Series	Acrylic Stainblocking Primer OR P009 Wood Alkyd Stainblocking Primer	0-7@85°	400	1.0	26	43	1 Hr.	4 Hrs.
	Latex	Satin	6000 Ext Series	(same)	5-15@60°	400	1.3	32	41	1 Hr.	4 Hrs.
	Alkyd	Semi-Gloss	9000 Int/Ext Series	(same)	70+@60°	400	2.2	54	72	4-5 Hrs.	12-18 Hrs.
	Latex	Semi-Gloss	7000 Ext Series	(same)	35-45@60°	400	1.3	32	43	1 Hr.	4 Hrs.
Floors, Dadoes, Platforms	Alkyd	Gloss	9300 Int/Ext Floor Enamel	None	85+@60°	400	2.2	55	68	6-8 Hrs.	24 Hrs.
Plywood	Latex	Flat	9500 Int/Ext Series	P007 All Surface	0-5@85°	400	1.3	32	43	1 Hr.	4 Hrs.
			5000 Ext Series	Acrylic Stainblocking Primer	0-7@85°	400	1.0	26	43	1 Hr.	4 Hrs.
	Latex	Satin	6000 Ext Series	(same)	5-15@60°	400	1.3	32	41	1 Hr.	4 Hrs.
	Alkyd	Semi-Gloss	9000 Int/Ext Series	(same)	70+@60°	400	2.2	54	72	4-5 Hrs.	12-18 Hrs.
	Latex	Semi-Gloss	7000 Ext Series	(same)	35-45@60°	400	1.3	32	43	1 Hr.	4 Hrs.

EXTERIOR METAL											
Surface & Area	Veh.	Sheen	Finished Coat	Primer	Gloss Units	Sq.ft./Gal. (smooth)	Mils DFT	% Solids By Vol.	% Solids By Wt.	Drying Time:	
										To Touch	To Recoat
Iron & Steel, Non-Galvanized, Galvanized, Doors, Vents, Ducts	Latex	Flat	9500 Int/Ext Series	P007 All Surface	0-5@85°	400	1.3	32	43	1 Hr.	4 Hrs.
			5000 Ext Series	Acrylic Stainblocking Primer	0-7@85°	400	1.0	26	43	1 Hr.	4 Hrs.
	Latex	Satin	6000 Ext Series	(same)	5-15@60°	400	1.3	32	41	1 Hr.	4 Hrs.
	Alkyd	Semi-Gloss	9000 Int/Ext Series	Metal Primer	70+@60°	400	2.2	54	72	4-5 Hrs.	12-18 Hrs.
	Latex	Semi-Gloss	7000 Ext Series	P007 All Surface Acrylic Stainblocking Primer	35-45@60°	400	1.3	32	43	1 Hr.	4 Hrs.
Aluminum	Latex	Flat	9500 Int/Ext Series	None	0-5@85°	400	1.3	32	43	1 Hr.	4 Hrs.
			5000 Ext Series	None	0-7@85°	400	1.0	26	43	1 Hr.	4 Hrs.
	Latex	Satin	6000 Ext Series	None	5-15@60°	400	1.3	32	41	1 Hr.	4 Hrs.
	Latex	Semi-Gloss	7000 Ext Series	None	35-45@60°	400	1.3	32	43	1 Hr.	4 Hrs.

EXTERIOR MASONRY											
Surface & Area	Veh.	Sheen	Finished Coat	Primer	Gloss Units	Sq.ft./Gal. (smooth)	Mils DFT	% Solids By Vol.	% Solids By Wt.	Drying Time:	
										To Touch	To Recoat
Cinder & Concrete Block	Latex	Flat	9500 Int/Ext Series	P9511 Acrylic Latex Block Filler OR P007	0-5@85°	400	1.3	32	43	1 Hr.	4 Hrs.
			5000 Ext Series	All Surface Acrylic Stainblocking Primer	0-7@85°	400	1.0	26	43	1 Hr.	4 Hrs.
	Latex	Satin	6000 Ext Series	(same)	5-15@60°	400	1.3	32	41	1 Hr.	4 Hrs.
	Alkyd	Semi-Gloss	9000 Int/Ext Series	(same)	70+@60°	400	2.2	54	72	4-5 Hrs.	12-18 Hrs.
	Latex	Semi-Gloss	7000 Ext Series	(same)	35-45@60°	400	1.3	32	43	1 Hr.	4 Hrs.
Concrete Floors, Patios, Steps, Platforms	Alkyd	Gloss	9300 Int/Ext Floor Enamel	None	85+@60°	400	2.2	55	68	6-8 Hrs.	24 Hrs.
Concrete Walls, Unglazed Brick, Stucco	Latex	Flat	9500 Int/Ext Series	P007 All Surface	0-5@85°	400	1.3	32	43	1 Hr.	4 Hrs.
			5000 Ext Series	Acrylic Stainblocking Primer	0-7@85°	400	1.0	26	43	1 Hr.	4 Hrs.
	Latex	Satin	6000 Ext Series	(same)	5-15@60°	400	1.3	32	41	1 Hr.	4 Hrs.
	Alkyd	Semi-Gloss	9000 Int/Ext Series	(same)	70+@60°	400	2.2	54	72	4-5 Hrs.	12-18 Hrs.
	Latex	Semi-Gloss	7000 Ext Series	(same)	35-45@60°	400	1.3	32	43	1 Hr.	4 Hrs.

Please refer to the Product Data Sheet for proper surface preparation and application guidelines.

For more information and your nearest retailer or representative, visit us at www.concopaints.com or call 1.888.388.2426